

Coupling Tension and Shear for Highly Sensitive Graphene-Based Strain Sensors

Zenan Qi¹, Jian Zhang², Guiping Zhang³ and Harold S. Park¹

¹*Department of Mechanical Engineering, Boston University, Boston, MA 02215*

²*Microsoft Corporation 15700 NE 39th St Redmond, WA 98052 and*

³*Department of Physics, Renmin University of China, Beijing 100872, China*

(Dated: August 28, 2015)

We report, based on its variation in electronic transport to coupled tension and shear deformation, a highly sensitive graphene-based strain sensor consisting of an armchair graphene nanoribbon (AGNR) between metallic contacts. As the nominal strain at any direction increases from 2.5 to 10%, the conductance decreases, particularly when the system changes from the electrically neutral region. At finite bias voltage, both the raw conductance and the relative proportion of the conductance depends smoothly on the gate voltage with negligible fluctuations, which is in contrast to that of pristine graphene. Specifically, when the nominal strain is 10% and the angle varies from 0° to 90°, the relative proportion of the conductance changes from 60 to ~90%.

Graphene has been proposed for many applications due to its unique physical properties [1–4], in which the electronic transport through graphene nanoribbon would be affected by line defect [5]. Of specific interest to the present work, it has been proposed as a strain sensor due to change in the conductivity of graphene-based materials [6–12]. The field of graphene-based strain sensing has rapidly developed since the experimental observation of the increase in resistance of CVD graphene samples when strain is applied in the direction of the electrical current [6]. In order to accurately determine the direction and magnitude of strain, a triaxial graphene-based strain sensor composite was proposed; it was found that the resistance of graphene may be enhanced or reduced by the strain in certain directions [7]. The sensitivity of graphene to strain originates from the deformation of carbon-carbon bonds, which alter the hopping integrals, and thus the electronic transport in graphene.

Though the effect of strain on the band structure of graphene and narrow graphene nanoribbons (GNRs) has been widely discussed [13–17], strain sensing based on electronic transport through graphene and GNRs has recently become of wide interest [18–24]. In the present work, motivated by recent experimental findings of the potential benefits of coupled tension/shear deformation to simulate the strain generated due to the movement of human fingers [7], we theoretically study coupled tension and shear deformation on the transport through armchair graphene nanoribbons between metallic contacts.

Most previous theoretical studies of graphene strain sensors have adopted homogeneous junctions. However, no lattice mismatch occurs at the interfaces for homogeneous junctions, whereas the conductance in unstrained GNRs is either zero or one at the Fermi energy $E = 0$ [25]. Unlike most experiments in which the gate voltage is only applied to graphene samples, the Fermi energy E should vary to investigate electronic transport through GNRs. For heterogenous junctions of GNRs between quantum wire contacts, transport through GNRs is mediated by the gate voltage V_g as in previous experimental measurement on electrical properties of graphene samples [1–3]. These heterogenous junctions are inspired by the




FIG. 1. (Color online.) (a) Schematic illustration of AGNRs, connected to two semi-infinite quantum wires. There are N and M carbon atoms in x and y directions, respectively. θ is the angle between the direction of applied strain S and x -axis. (b) The tensile and (c) the shear component of the strain at 30° when the nominal strain is $\epsilon_{n,s} = 10\%$.

fact that the contacts are metallic rather than carbon in experiments [1–3] and the conductance of quantum wire contacts is maximal at $E = 0$ because all channels are available to electronic transport.

However, lattice mismatch may exist at the interfaces of heterogeneous junctions. Here we adopt heterojunctions of armchair-edged GNRs (AGNR) between quan-

tum wire contacts as discussed in Ref. [26] to minimize the effect of lattice mismatch at the interfaces and investigate the effect of uniaxial plus shear strain on electronic transport as illustrated in Fig. 1. The strain is only applied to the AGNR and impacts the hopping integrals in the AGNR. The hamiltonian of the AGNR and contacts is described by the tight binding approximation as

$$\hat{H} = \sum_{\langle ij, i'j' \rangle} t_{ij, i'j'} \hat{c}_{ij}^\dagger \hat{c}_{i'j'} + V_g \sum_{ij} \hat{c}_{ij}^\dagger \hat{c}_{ij}, \quad (1)$$

where a pair of integers ij indicates the lattice position \vec{R}_{ij} , and \hat{c}_{ij} (\hat{c}_{ij}^\dagger) is the electron annihilation (creation) operator. The summation is over the nearest neighbors indicated by $\langle \dots \rangle$. $t_{ij, i'j'}$ is the hopping integral between nearest-neighboring sites indexed by ij and $i'j'$. V_g is the effective gate voltage applied to graphene, which is zero in contacts. When V_g slightly varies at the interfaces, the conductance does not change much around $V_g = 0$ [27].

The deformed configurations of the graphene nanoribbons were obtained by molecular mechanics simulations, where the strain was obtained via applied displacement loading [21, 28]. The rectangular AGNR consisted of 2832 atoms with a length of $L = 10.224$ nm and width $W = 7.018$ nm. Displacements were applied in increments of 0.01\AA followed by a subsequent energy minimization and relaxation until the change in system energy was less than 10^{-7} compared with the previous step. The simulations were performed using the open source package LAMMPS [29], and the AIREBO interatomic potential [30] with a cutoff of 0.68nm . This potential has been shown to accurately describe carbon-carbon interactions resulting in accurate predictions of the mechanical properties of graphene [31]. We note that because molecular mechanics simulations were performed, which are intrinsically at 0K , and because all applied displacements were in-plane, there was no out-of-plane buckling during the simulation.

As shown in Fig. 1 (b,c), coupled tension and shear were applied onto AGNRs and the corresponding strains were calculated as discussed in previous works [21]. We also define the ‘nominal strain’ as the displacement applied (regardless of the direction) with reference to the original length. Once the carbon atomic positions are obtained at each value of strain, the hopping along each bond (with the length l) $V_{pp\pi} = t_0 e^{-3.37(l/a-1)}$ [13] ($t_0 = 2.7$ eV and $a = 0.142$ nm) is used as the basis for the electronic structure and quantum transport calculations. Due to the 2D nature of our analysis, σ bonds were not considered in our calculation.

Strain was applied with a tilted angle θ (Fig. 1) from 0° to 90° at five different angles, i.e. 0° , 30° , 45° , 60° and 90° , where 0° loading represents pure tension, 90° represents pure shear and the other three couple tension and shear. To simplify the notation, we also introduce a ‘nominal strain’ ϵ_{ns} , which is defined as the displacement applied over the original nanoribbon length regardless of the loading angle. All cases with different loading angles are deformed at three stages, namely




FIG. 2. (Color online.) The current through AGNR depends on the bias voltage V_b at $V_g = 0$ (a) and $V_g = t_0$ (b). The conductance of AGNR changes with V_b at $V_g = 0$ (lower lines) and t_0 (upper symbols) (c), and with the gate voltage in AGNR at $V_b = 0$ and $V_b = 0.2t_0$ (d). No strain is applied (black line) and the nominal strain ϵ_{ns} being 10% is applied at 0° (red line), 30° (green line), 60° (blue line) and 90° (magenta line) respectively. The size of AGNRs is $M = 29$ and $N = 96$. V_b and V_g in figures is in the unit of t_0 .

$\epsilon_{ns} = 2.5\%, 5\%, 10\%$, and we will refer exclusively to ϵ_{ns} in the following. The tension (ϵ_{xx}) and shear (ϵ_{xy}) strain components at the three stages for different loading angles are corresponding as: $\epsilon_{xx} = 2.5\%, 5\%, 10\%$ and $\epsilon_{xy} = 0\%, 0\%, 0\%$ for 0° ; $\epsilon_{xx} = 2.1\%, 4.1\%, 8.7\%$ and $\epsilon_{xy} = 0.5\%, 0.9\%, 1.8\%$ for 30° ; $\epsilon_{xx} = 1.6\%, 3.3\%, 7.8\%$ and $\epsilon_{xy} = 0.7\%, 1.4\%, 2.6\%$ for 45° ; $\epsilon_{xx} = 1.1\%, 2.4\%, 7\%$ and $\epsilon_{xy} = 0.9\%, 1.8\%, 3.1\%$ for 60° ; $\epsilon_{xx} = 0\%, 0\%, 0\%$ and $\epsilon_{xy} = 1.1\%, 2.2\%, 3.7\%$ for 90° . The deformed atomic configuration and the resulting components of the tensile and shear strain at 30° when the nominal strain is $\epsilon_{ns} = 10\%$ is shown in Fig. 1(b) and (c) [32]. The left contact is fixed while the right one is shifted with strain similar to Ref. [9] when the shear strain is present, and the hopping integral in contacts and interfaces are not affected by the shear/tension.

At a finite bias voltage V_b , the current transfer from the left contact to the right one is expressed as $I(S, V_b, V_g) = 2e/h \int_{E_f - V_b/2}^{E_f + V_b/2} T(S, E, V_g) dE$ [34], where S refers to the strain and $S = 0$ stands for no deformation in the GNR, e is the electron charge and h is Planck’s constant. $T(S, E, V_g)$ is the transmission at the strain S , the energy E and the gate voltage V_g . Since the effect of the gate voltage on the strain sensor has been explored in a dual-gate setup [9], we include V_g to estimate the stability and applicability of the graphene-based strain sensor. Based on the tight binding hamiltonian in Eq.(1) and the transfer matrix method, the transmission $T(S, E, V_g)$ is obtained through the scattering matrix by solving the Schrödinger equations, which is described in detail in Refs. [36, 37].

$I(S, V_b, V_g)$ at $V_g = 0$ at first increases slowly and then sharply with V_b as shown in Fig. 2 (a), since the transmission increases as the GNR deviates from being electrically neutral, which has the lowest density of states [24]. $I(S, V_b, V_g)$ at $V_g = t_0$ at first increases linearly and then sub-linearly with V_b as shown in Fig. 2 (b), since the transmission decreases as GNR deviates from the highest density of states [24]. The conductance is defined as $G(S, V_b, V_g) = I(S, V_b, V_g)/V_b$, and is directly related to the transmission at Fermi energy $T(S, E_f, V_g)$ at the limit of $V_b \rightarrow 0$ [34]. The conductance $G(S, V_b, V_g)$ slightly increases and decreases at $V_g = 0$ and $V_g = t_0$ respectively when V_b increases, as shown in Fig. 2(c). When V_g changes, a large oscillation of the conductance at $V_b = 0$ is induced by quantum interference when electrons are reflected at the GNR-contact interfaces [24, 26, 35–37], and electron-hole asymmetry in conductance is originated by odd-numbered rings at the interfaces as shown in Fig. 1 [26]. The curve of the conductance versus the gate voltage at $V_b = 0.2t_0$ overlaps the one at $V_b = 0$ and the fluctuation becomes invisible, as shown in Fig. 2(d), due to the summation of the transmission among the energy range $[E_f - V_b/2, E_f + V_b/2]$.

In strained AGNRs, the transport depends on both the direction and magnitude of the strain S . When the nominal strength of the strain is 10%, the current at both zero and finite V_g is lower than in undeformed AGNR, and gradually increases with the change in angle of the applied strain, when the strain varies from 0° to 90° combined with shear, as shown in Fig. 2(a,b). Under pure tension at 0° , the change in the current completely reproduces the observation [6]. The slope of the I - V_b curve (i.e., the conductance) for nearly electrical neutral graphene samples, which corresponds to our result at $V_g = 0$ and which is dependent on the specific experimental setup, is $1.5 \times 10^{-4} \Omega^{-1}$ [6] and $2 \times 10^{-5} \Omega^{-1}$ [7]. Our results show that the ballistic conductance of the 7.018 nm wide AGNR is around $3 \times 10^{-5} \Omega^{-1}$ and $1 \times 10^{-3} \Omega^{-1}$ at $V_g = 0$ and $V_g = t_0$ respectively. The conductance dependence on the strain shown in Fig. 2(c) is the same as the current dependence on the strain.

We compare the conductance dependence on pure tension and pure shear at 90° to estimate the effect of tension and shear on transport through AGNR. On one hand, in contrast to the fact that the conductance at $-t_0 < V_g < 0.5t_0$ under pure tension at 90° is higher than undeformed AGNRs as a result of an increase in the hopping integrals along the horizontal direction [24], the conductance under pure shear at 90° is always lower than that in undeformed AGNRs as $|V_g| \geq 0.5t_0$ except for some fluctuations as shown in Fig. 2. Our calculation is consistent with the observation of the conductance dependence on the shear strain [9]. On the other hand, the conductance around the neutral point (i.e., at small $|V_g|$) increases with the angle of tension/shear as shown in Fig. 2(c), compared with that under pure tension at 0° . The maximal conductance of undeformed AGNR being MG_0 ($G_0 = 2e^2/h$) occurs at $E = \pm t_0$ and $V_g = 0$




FIG. 3. (Color online.) The ratio of the conductance in AGNRs before and after application of the strain with the nominal strain being 10% (a) and the nominal strain is 2.5%, 5% and 10% at an angle of 0° (b), 45° (c) and 90° (d) between x -axis. The size of AGNR is $M = 29$ and $N = 96$. The bias voltage is $V_b = 0.2t_0$ (main panels) and $V_b = 0$ (insets).

between graphite contacts and at $E = 0$ and $V_g = t_0$ between quantum wire contacts. The maximal conductance of strained AGNR around $V_g = t_0$ decreases as a result of deformation in AGNR when tension and/or shear is applied to AGNR. The data indicates that electronic transport through AGNR can be easily mediated by the strain when the system deviates from the electrically neutral region.

In most experiments of graphene-based strain sensors [6, 7], no gate voltage is applied and graphene may not be electrically neutral due to the doping from metallic contacts [9, 38]. Recently the effect of the gate voltage has been explored [9], and thus we set the gate voltage as a variable parameter to provide information such as the stability of the strain sensor under different gate voltages. The change of current is usually measured under strain and the percentage of the resistance is used to estimate the effect of the strain on transport through graphene samples [6, 7]. Therefore, we use the ratio of the conductance compared with that in undeformed AGNR, $G(S, V_b, V_g)/G(0, V_b, V_g)$, to measure the sensitivity of the graphene-based strain sensor as shown in Fig. 3.

Due to large oscillations in the conductance at $V_b = 0$, a large oscillation is also seen in the ratio $G(S, V_b, V_g)/G(0, V_b, V_g)$ as shown in the insets of Fig. 3. However, the trends of $G(S, V_b, V_g)/G(0, V_b, V_g)$ are still clear. The conductance ratio at $V_b = 0.2t_0$ shown in the main panels of Fig. 3 is relatively smooth at negative gate voltage, shows a large dip or peak around zero gate voltage and slightly decreases as the gate voltage becomes more positive. When the nominal strain is 10% in Fig. 3(a), the conductance slightly increases but is smaller than in the undeformed case, as the angle θ varies

from 0° to 90° . As θ is varied from 0° , 45° and 90° in Figs. 3(b-d), the conductance decreases as the nominal strain increases from 2.5% to 10%. It is found that the conductance shows little change under pure shear at 90° as shown in Fig. 3(d). We demonstrate that this kind of strain sensor is robust since the relative proportion of the conductance is smooth within a wide gate voltage range [1, 2].

In summary, we have studied a graphene-based strain sensor consisting of armchair graphene nanoribbon (AGNR) between metallic contacts in response to combined tension/shear. The conductance and the relative proportion of the conductance decreases as the strain increases. This kind of strain sensor has relatively higher sensitivity to the strength of the strain at finite bias volt-

age and a wide range of the gate voltage when the strain is parallel to the armchair edge.

Finally we comment on the performance of a strain sensor made from a zigzag graphene nanoribbon (ZGNR) between quantum wire contacts with a possible lattice mismatch at the interfaces. Compared with the case of AGNR, the fluctuation of the conductance of ZGNR is larger, when the gate voltage changes. The ratio of the conductance, $G(S, V_b, V_g)/G(0, V_b, V_g)$, ranges between 0.8 and 1.4 as $|V_g| \leq 2t_0$, and the dependence of the conductance ratio on the strain are different from that seen in Fig. 3 when $|V_g| \leq t_0$.

Acknowledgements HSP and ZQ acknowledge support from the Mechanical Engineering and Physics Departments at Boston University. G. P. Zhang thanks support by NSF of China (Grant No. 11204372).

-
- [1] Novoselov K S, Geim A K, Morozov S V, Jiang D, Zhang Y, Dubonos S V, Grigorieva I V and Firsov A A 2004 Science 306, 666
 - [2] Novoselov K S, Geim A K, Morozov S V, Jiang D, Katsnelson M I, Grigorieva I V, Dubonos S V and Firsov A A 2005 Nature (London) 438, 197
 - [3] Miao F, Wijeratne S, Zhang Y, Coskun U C, Bao W and Lau C N, 2007 Science 317 1530
 - [4] Schedin F, Geim A K, Novoselov K S et al 2007 Nature Materials 6, 652-655
 - [5] Dutta P, Maiti S K and Karmakar S N 2013 J. Appl. Phys. 114(3), 034306.
 - [6] Fu X W, Liao Z M, Zhou J X, Zhou Y B, Wu H C, Zhang R, Jing G Y, Xu J, Wu X S, Guo W L and Yu D P 2011 Appl. Phys. Lett. 99, 213107
 - [7] Bae S H, Lee Y, Sharma B K, Lee H J, Kim J H and Ahn J H 2013 Carbon 51, 236
 - [8] Chun S, Kim Y, Jin H, Choi E, Lee S B and Park W 2014 Carbon 78, 601-608
 - [9] He X, Gao L, Tang N et al 2014 Appl. Phys. Lett. 105, 083108
 - [10] Wang Y, Wang L, Yang T T et al 2014 Adv. Funct. Mat. 24, 4666-4670
 - [11] Souma S, Ohmi Y, Ogawa M 2013 J. Comput. Electr. 12, 170-174
 - [12] Mohammad Reza Moslemi, Mohammad Hossein Sheikhi, Kamyar Saghaei, Mohammad Kazem Moravvej-Farshi 2012 Microelectronics Reliability 52, 2579-2584
 - [13] Pereira V M, Neto A H Castro and Peres N M R 2009 Phys. Rev. B 80, 045401
 - [14] Li Y, Jiang X W, Liu Z F and Liu Z R 2010 Nano Res. 3, 545
 - [15] Peng X, Tang F and Copple A 2012 J. Phys.: Condens. Matter 24, 075501
 - [16] Lu Y and Guo J 2010 Nano Res. 3, 189
 - [17] Sena S H R, Pereira Jr J M, Farias G A, Peeters F M and Costa Filho R N 2012 J. Phys. Condens. Matter, 24(37), 375301
 - [18] Poetschke M, Rocha C G, Torres L E F Foa, Roche S and G. Cuniberti 2010 Phys Rev B 81, 193404
 - [19] Wang J Y, Liu Z F and Liu Z R 2012 AIP Advances 2, 012103
 - [20] Rasuli R, Rafii-Tabar H and Zad A I 2010 Phys Rev B 81, 125409
 - [21] Qi Zenan, Bahamon D A, Perira Vitor M, Park Harold S and Campbell D K 2013 Nano Lett. 13, 2692-2697
 - [22] Bahamon D A and Pereira V M 2013 Phys. Phys. Rev. B 88, 195416
 - [23] Cosma Diana A, Mucha-Kruczycki Marcin, Schomerus Henning and Vladimir I. Fal'ko 2014 Phys. Rev. B 90, 245409
 - [24] Wang J, Zhang G P, Ye F and Wang X Q arXiv:1411.1529
 - [25] Peres N M R, Castro Neto A H and Guinea F 2006 Phys Rev B 73, 195411
 - [26] Zhang G P and Qin Z J 2011 Chem. Phys. Lett. 516, 225
 - [27] Wang J, Zhang G P, Ye F and Wang X Q unpublished.
 - [28] Qi Z, Campbell D K and Park Harold S 2014 Phys. Rev. B 90, 245437
 - [29] <http://lammps.sandia.gov> (2012); Plimpton S 1995 J. Comput. Phys. 117, 1
 - [30] Stuart S J, Tutein A B and Harrison J A 2000 J. Chem. Phys. 112, 6472
 - [31] Zhao H, Min K, Aluru N R 2009 Nano Lett. 9, 3012-3015; Wang M et al 2012 Comput. Mater. Sci 54, 236-239
 - [32] Qi Z, Kitt Alexander L, Park Harold S, Pereira Vitor M, Campbell David K and Neto A H Castro 2014 Phys. Rev. B 90, 125419
 - [33] Los J H, Katsnelson M I, Yazyev O V, Zakharchenko K V and Fasolino A 2009 Phys. Rev. B 80, 121405
 - [34] Büttiker M, Imry Y, Landauer R and Pinhas S 1985 Phys. Rev. B 31, 6207
 - [35] Yin Y and Xiong S J 2003 Phys. Lett. A 317, 507
 - [36] Hu S J, Du W, Zhang G P, Gao M, Lu Z Y and Wang X Q 2012 Chin. Phys. Lett. 29, 057201
 - [37] Gao M, Zhang G P and Lu Z Y 2014 Comput. Phys. Commun. 185, 856
 - [38] Giovannetti G, Khomyakov P A, Brocks G, Karpan V M, Brink J van den and Kelly P J 2008 Phys. Rev. Lett. 101, 026803